

A New Generation of SnO2 gas sensor for agro-industrial applications

Philippe Menini, S Cornibert, André Maisonnat, Laurent Erades, M.

Guerrero, Bruno Chaudret, A. Martinez

▶ To cite this version:

Philippe Menini, S Cornibert, André Maisonnat, Laurent Erades, M. Guerrero, et al.. A New Generation of SnO2 gas sensor for agro-industrial applications. 3rd European Conference on Odours metrology and Electronic Noses (Eurodeur-Airodeur), Jun 2001, Paris, France. hal-02160612

HAL Id: hal-02160612 https://laas.hal.science/hal-02160612

Submitted on 19 Jun2019

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

A New Generation of SnO₂ gas sensor for agro-industrial applications

Ph. Ménini¹, S. Cornibert¹, A. Maisonnat², L. Erades², M. Guerrero¹, B. Chaudret² and A. Martinez¹

¹ LAAS-CNRS, 7 av. Colonel Roche 31077 Toulouse cx 4, France ² LCC-CNRS, 205 route de Narbonne 31077 Toulouse cx 4, France

Abstract

A new generation of gas sensor which consists of a silicon platform with an integrated polysilicon resistor as heater and a nanoparticular SnO_2 sensitive layer has been developed and characterized. Methods of deposition and oxidation of the sensitive layer on the substrate were first optimized. Then, a demonstrator was implemented to evaluate the sensor's electrical behaviour under controlled atmospheric conditions. An electrical circuit has been developed to model the electrical behaviour of the sensor. Comparisons between PSPICE simulations and experimental data shows close agreement.

Introduction

Many industrial applications are based on gas detection like individual safety or comfort purpose : for example, H_2S detection in chemical industries, household combustion alarm with CO and H_2 monitoring, cabin quality control in cars (CO, NO_x), emission control of small ozone generators (O₃), industrial health monitoring (NO_x), control of ethylene emission by fruits and/or vegetables in cold storage among others. In order to satisfy to this increasing demand, the actual market offers mainly three basic types of gas sensors for such toxic gas detection :

- Optical infrared sensors (IRGS)

- Electrochemical cells (ECGS)

- Solid state or semiconductors gas sensors (SGS).

In Europe, Japanese Companies sell more than 85% of all SGS used. SGSs offer many advantages : they are from far the least costly class of gas sensors and their properties (sensitivity, long operational life, low power consumption) make them very well suited for a multitude of applications.

An extended international work has been yet focused on new compositions for oxide active layer (ZnO, WO_3 , TiO₂, mixed oxides, etc...), but little on the microstructure of the sensitive material itself, since commercial SGSs are still based on standard metal oxide powders. Therefore, SGSs are mainly dealing with tin oxide as sensitive material.

Ethylene has been identified as a phyto-hormone in the process of fruits maturation. Therefore, presence of ethylene closeness of the fruit means that this fruit has already started its maturation phase. So, it can't be kept in stock. Actually, fruit storage rooms are not equipped with gas sensor systems which could allow the control of ethylene concentration in situ and in real time. Only heavy spectroscopy or optical chromatography methods exist to analyse each gas present in the stocking room.

In this context, in collaboration with regional chemists (LCC-CNRS), biologists (INPT-INRA), microtechnologists (LAAS-CNRS) and MICS (Microchemical Systems) firm, a new generation of SGS based on nanoparticular sensitive layer integrated on a silicon platform has been developed.

After a brief description of different parts of these new gas sensors, test methodologies will be presented.

Sensor description

The detection principle is based on the chemical reaction in air of the heated tin oxide surface with reducing or oxidising gas molecules, giving rise to the modulation of the electrical resistance of the sensitive layer. The known drawback of this device is linked to the stability of the baseline resistance over time and generally the cross sensitivity (or selectivity) to many gases and vapours (humidity, H_2 , Ethanol,...). This is due to the technology, which mainly relies on basic ceramic processes i.e. sintered tin oxide powders with a bead shape or deposited onto alumina substrates (fig. 1a, 1b).



<u>Fig. 1: Commercial semiconductor gas sensor</u>: a) sintered ceramic of gas sensitive material. b) thick sensitive film on alumina substrate

Moreover, it has been also demonstrated that more dispersed matter like nano-particles offers a high surface to volume ratio, correlated with better sensing properties than conventional matter. Microelectronics technology based on **silicon processing and specially on micro-machining** is known to offer **high miniaturisation and integration** possibilities.

This new technology will offer low cost products, high miniaturisation level (operational dice $< 1 \text{ mm}^2$), very low power consumption, and better sensing properties, stability and selectivity due to nano-sized oxide particles. Our SGS process is based on three main steps :

i) **Fabrication of silicon chips with all integrated structures** (heater, metal connections, membrane). A first design has been realised and operational dice have been assembled. This structure can be extended to the production of a muli-sensor platform (two or more sensitive areas per single chip).





Thermal activation of homoleptic tin amido complexes in organic solvents containing controlled traces of water yields spherical nanoparticular composites of 20 nm diameter, constituted of a tin β core surrounded

by a protecting tin oxide layer. These Sn/SnOx nanocomposites are thermally oxidised in air to yield crystalline SnO2 nanoparticules without modification of size or size distribution.



Figure 3 : Syntheses of tin nanoparticules

Two-drop deposition techniques are currently under investigation and have led to realise several hundreds of operational sensors. One of them is described on figure 4.



iii) Packaging the sensor with a new generation of active filters made of meso-porous materials in order to improve the selectivity.

Characterization

Before test sequences, the sensors have to be subjected to at least one heating cycle from 25° C to 450° C. Their optimal work temperature has been estimated around 400° C. A temperature of 450° C must not be exceeded to avoid problem of electromigration from metal through polysilicon on contact pads.

Electrical Behaviour

A specific mock-up has been realised to allow DC and AC measurements on the sensitive layer with the heater resistor powered from 0 to 2.5V.

Figure 5 shows an example of different sensors DC responses which represents the resistance of the sensitive layer versus temperature. It clearly appears that the new sensor (curve with diamonds) presents a resistivity four times smaller than that of the traditional sputtered tin oxide sensor (curve with full-squares). Moreover, a local maximum appears for temperature near 320°C. This phenomena is partially attributed to humidity rate ^[6]. Therefore, these kind of electrical tests permit to predict that the new sensor has a better sensitivity than the others.



AC measurements constitute the second part of the sensor's electrical behaviour study. A 7600Quadteck impedance meter were used to achieve measurements versus frequency from 10 to 2 MHz. Real and imaginary parts have been extracted and shown in fig. 6. It can be made the comparison between frequency behaviour of three different kinds of sensitive layer. The curve with diamonds represents the nanoparticular Sn02 while the one with squares represents the traditional sputtered SnO2. The third curve with triangles points out an hybrid sensitive layer behaviour elaborated from both aforesaid processes.



Figure 6 : Impedance measurements : a) Real part vs frequency ; b) Imaginary part vs frequency

In this range of frequency, according to PSPICE simulations, the three of the sensors can be modelled by the same equivalent circuit shown in figure 7. In fact, different values of each parameter permit to fit with experimental data of each sensors. Same measurements with different operating temperature reveal that all of the circuit parameters present the same temperature dependency.



Figure 7 : Equivalent circuit of the encapsulated SnO₂ gas sensor.

Behaviour under ethylene

The detection principle is well known, based on the chemical reaction in air of the heated tin oxide surface with reducing gas molecules giving rise to the modulation of the electrical resistance of the sensitive layer.



Figure 8 : Sensitive layer resistance variation with different injections of ethylene ; a) in dry air -b) with 25% HR

Figure 8 shows the nanoparticular sensitive layer resistance variation with different ethylene concentration. All these measurements have been made with constant operating temperatures.

In dry air, it can be seen first that these sensors are reversible and reproducible. In these conditions (0%RH, T=420°C) the detection limit has been evaluated around 0.6 ppm and the sensitivity defined by the ratio Rs(10ppm)/Rs(0) reaches 53%. In humid air with just 25% RH, this sensitivity decreases to only 5%. On the other hand, the sensitivity (at 10 ppm and 25%RH) can be increased again up to 30% if the operating temperature is pulsed as it is shown in figure 9. In this case, the sensitivity is defined by the ratio $\Delta Rs(10ppm)/\Delta Rs(0)$ at the hot level.



Figure 9 : Resistance of sensitive layer versus time with pulsed operating temperature

Conclusion

This paper allows the comparison of several characteristics between sensors based on standard SnO_2 sensitive layer with those elaborated with nanometer-scaled sensitive layers which use metal oxide nanoparticles.

An electrical study of three different sensitive layers reveals that they can be modelled by the same equivalent circuit.

Experimental results under ethylene indicate that the colloidal SnO_2 presents better features than those of the traditional SnO_2 : first, the resistivity of the material is at least 4 times smaller. Then, the sensitivity is also better as it is possible to detect C_2H_4 concentrations lower than 1 ppm in dry air. Even if humidity degrades sufficiently the sensitivity, a dynamic mode of temperature operation minimizes this dependency. The sensitivity of this new generation of gas sensor is already (without any doping process) between 3 and 5 times better than actual commercial sensors.

Acknowledgements

This work is actually supported by the "Qualifel" Regional Program to improve quality of fruits and vegetables. We would like to thank Pierre Fau, Engineer from MicroMechanical Systems Inc. for his permanent collaboration and continuous encouragement.

Bibliography

[1] Stéphane Astié

Intégration d'un capteur de gaz à oxyde semi-conducteur sur silicium. French Theses, Université Paul Sabatier, Toulouse, France. 1998.

[2] Céline Nayral

Réalisation d'une nouvelle génération de capteurs de gaz utilisant des nanoparticules de dioxyde d'étain. French Theses, Université Paul Sabatier, Toulouse, France. 1999.

- [3] C. Nayral, A. Maisonnat, B. Chaudret, P. Fau Method of forming metal colloids and method of forming metal oxide nanoparticles used as sensitive layer for a chemical sensor device Eurpean Patent, Motorola, filing n° 98400246.9; filing date 5.2.98
- [4] C. Nayral, T. Ould-Ely, A. Maisonnat, B. Chaudret, P. Fau, L. Lescouzeres, A. Peyre-Lavigne A novel mechanism for the synthesis of Tin/Tin oxide nanoparticles of low size dispersity and of nanostructured SnO₂ Advanced Materials, vol 11, 1999, pp 61-63
- [5] P. Fau, M. Sauvan, S. Trautweiler, C. Nayral, L. Erades, A. Maisonnat, B. Chaudret Nanosized tin oxide sensitive layer on a silicon platform for domestic gas applications Sensors and Actuators B, 3955, 2001, pp 1-6
- [6] G. Korotchenkov, V. Brynzari, S. Dmitriev, Electrical Behaviour of SnO2 Thin Films in Humid Atmosphere Sensors and Actuators B, 54, 1999, pp 197-201